

Table 4 The chemical resistance of Perspex® from Lucite® cast clear at 20°C
The following symbols have been used in the table:-

S = Satisfactory (no apparent effect apart from possible staining)

A = Some attack evident (swelling or slight crazing)

U = Unsatisfactory (the sample has dissolved, swollen, decomposed, etc.).

CHEMICAL	CONCENTRATION	RESISTANCE	EXPOSURE TIME	NOTES
Acetic acid	10%	S	5 years	
	100%	U	1 day	Badly swollen
	Glacial	U	3 days	Dissolved
Acetone	100%	U	1 day	Dissolved
Alcohols, n-butyl		U	1 year	Crazing and disintegration
	Ethyl	10%	A	Slight attack
		50%	A	Slight attack
		100%	U	Slight swelling and softening
Isopropyl	10%	A	1 year	Crazing
	50%	A	1 year	Crazing
	100%	A	1 year	Attacked
Methyl	10%	A	1 year	Slight attack
	50%	A	168 days	Swollen
	100%	U	168 days	Swollen: weight increase
Ammonia	0.880 sol.	S	1 year	
Amyl acetate		U	28 days	Dissolved
Aniline		U	7 days	Dissolved
Aviation fuel	100-octane	A	168 days	Slight crazing
Benzaldehyde		U	7 days	Dissolved
Benzene		U	10 days	Dissolved
Calcium chloride	Saturated sol.	S	3 days	Slight attack
Carbon tetrachloride		U	84 days	Dissolving
Chloroform		U	1 day	Dissolved
Chlorine	2% in water	A	5 years	Surface crazing and attack
Chromic acid	10%	S	5 years	Stained
	Saturated sol.	U	1 year	Dissolving
Citric acid	Saturated sol.	S	5 years	
Dibutyl phthalate		A	2 years	Surface crazed
Diethyl phthalate		A	2 years	Slight attack
Dibutyl sebacate		A	2 years	Slight attack
Diethyl ether		U	168 days	Swollen & Soft
Ethylene glycol		S	5 years	
Ethylene dichloride		U	1 day	Dissolved
Ethyl acetate		U	3 days	Dissolved
Epichlorhydrin		U	1 day	Dissolved
Formaldehyde	40%	S	5 years	
Formic acid	10%	S	5 years	
	90%	U	7 days	

Workshop Handbook

CHEMICAL	CONCENTRATION	RESISTANCE	EXPOSURE TIME	NOTES
Glycerol (glycerine)		S	5 years	
Hexane		S	168 days	Slight crazing
Hydrochloric acid	10% Conc.	S	168 days	Slight crazing
		S	168 days	Slight crazing
Hydrocyanic acid		U	1 day	Dissolved
Hydrofluoric acid	Conc.	U	1 day	Swollen & Soft
Hydrogen peroxide	10 vol.	S	1 year	
	90%	U		
Mercury		S	2 years	
Methylene chloride (dichloromethane)		U	1 day	Dissolved
Methyl salicylate		U	7 days	Dissolved
Nitric acid	10% Conc.	S	1 year	
		U	1 day	Swollen
Oils - transformer		S	5 years	Staining
- diesel		S	1 year	Hazing
- olive		S	5 years	Slight crazing
-paraffin (medicinal)		S	5 years	
- silicones		A	1 year	Swollen
Oxalic acid	Saturated sol.	S	5 years	Severe crazing
Perchloroethylene		U	5 years	Severe crazing
Phenol	Saturated sol.	U	7 days	Dissolved
Phosphoric acid	10% Conc.	S	5 years	
		U	7 days	Severe crazing
Potassium dichromate	10%	S	5 years	Slight staining
Potassium hydrozide	Saturated sol.	S	168 days	
Potassium permanganate	N/10 sol.	S	5 years	Severe staining
Sodium carbonate	Saturated sol.	S	5 years	
Sodium chlorate	Saturated sol.	S	5 years	
Sodium hydroxide	Saturated sol.	S	5 years	
Sodium hypochlorite	10% chlorine sol.	S	5 years	
Sulphoric acid	10%	S	5 years	
	30%	S	1 year	Slight edge attack
	Conc.	U	1 day	Swollen
Tartaric acid	Saturated sol.	S	5 years	
Toluene		U	7 days	Dissolved
Trichloroethane		U	1 day	Dissolved
Trichlorethylene		U	1 day	Dissolved
Tricresyl phosphate		U	2 years	Attacked/crazed
Water		S	5 years	
White Spirit		S	5 years	Slight crazing
Xylene		U	7 days	Dissolved

NOTE:

Chemical resistance tests are difficult to interpret accurately because plastics materials generally may be attacked in several ways. The table must therefore be used with discretion and should be supplemented by component tests under actual service conditions.



ALLPLASTICS ENGINEERING PTY LTD

*Unit 20, 380 Eastern Valley Way
CHATSWOOD NSW 2067*

Tel: (02) 9417 6111

Fax (02) 9417 6169

Email: sales@allplastics.com.au

Web: www.allplastics.com.au

***Specialist in Machining,
Fabrication & Supply of Plastics***