

KS Polyolefin-Adhesive-Set

Chemical properties in liquid state

	K+S MULTI-PURPOSE ADHESIVE MAGNUMBOND	K+S POLYOLEFIN-PRIMER
Chemical base:	Ethylcyanoacrylate	Aliphatic amine in solvent
Colour:	Colourless	Colourless
Density at 25°C:	LOS	0.68
Viscosity, mPa-s:	10-30	0.5-2
Flashpoint (COC), °C:	80	-1
Vapour pressure, mbar:	< 1	50
Storage life at 20°C (Month)	12	12
Solvent	-	Heptane
Drying time at 20°C (Seconds)	-	30
Open time (hours):	-	8
Fluorescence in UV light (Low intensity, 365nm):	-	Yes
Toxicity:	Low	Low