

SIMOPOR-LIGHT

| | |
|--|--------------------------------|
| Density, g/cm ³ , ISO 1183 | 0.57 |
| Yield stress, MPa, DIN EN ISO 527 | 16 |
| Elongation at yield, %, DIN EN ISO 527 | 3 |
| Tensile modulus of elasticity, MPa, DIN EN ISO | 900 |
| Impact strength, kJ/m ² , DIN EN ISO 179 | 14 |
| Mean coefficient of linear thermal expansion, K ⁻¹ , DIN 53752 | 0,8 × 10 ⁻⁴ |
| Fire behaviour DIN 4102 | B1 low flammability 3 to 19 mm |
| Fire behaviour NF P 92-501 | M1 from 3 to 10 mm |
| Surface resistivity, Ohm, DIN IEC 60093 | >10 ¹⁵ |
| Temperature range, °C | 0 to +60 |
| Physiological safety in accordance with BfR | no |
| Physiological safety in accordance with EU | no |
| Physiological safety in accordance with FDA | no |

All specifications are deemed to be approximate values and may vary depending on the processing methods used and the specimen or test piece. In general, data specified applies to average values measured on extruded sheets with a thickness of 4mm. Deviations from the values specified are possible if the sheets in this thickness are not available. Information presented herein cannot necessarily be applied to finished items or products. Suitability of materials for a specific field of application must be assessed by the party responsible for processing or the end-user. All technical specifications presented herein are designed merely to provide assistance in terms of project planning. Under no circumstances do they constitute a guaranteed property or quality of the items presented.



Tel. (02) 8038 2000 Fax. (02) 9417 6169 Email. sales@allplastics.com.au

Address. Unit 20/380 Eastern Valley Way, Chatswood, NSW 2067 AUSTRALIA. www.allplastics.com.au